## **EUROPEAN PATENT OFFICE**

## **Patent Abstracts of Japan**

**PUBLICATION NUMBER** 

58199822

**PUBLICATION DATE** 

21-11-83

**APPLICATION DATE** 

15-05-82

APPLICATION NUMBER

57082281

APPLICANT: NIPPON STEEL CORP;

INVENTOR: ASHIURA TAKEO;

INT.CL.

C21D 9/46 C21D 8/02 // C22C 38/26

TITLE

MANUFACTURE OF FERRITIC STAINLESS STEEL SHEET CAUSING NO RIDGING

ABSTRACT :

PURPOSE: To improve the ridging resistance of a steel contg. Nb and having a single ferrite phase and to prevent thoroughly ridging by repeating recrystallization including at

the time of hot rolling.

CONSTITUTION: The composition of a ferritic stainless steel is composed of, by weight, <0.015% C, 0.015~0.035% N, 0.2~1% Nb, 10~22% Cr and the balance Fe with inevitable impurities while satisfying Nb>(C+N)×8. A slab of the steel is heated at 1,100~1,250°C and hot rolled at ≥1,000°C at ≥30% draft per one pass. The hot rolled plate is annealed at 900~1,100°C for ≤10min and cooled. The plate is optionally process-annealed once or more, and it is cold rolled and subjected to recrystallization

annealing.

COPYRIGHT: (C)1983,JPO&Japio